

## B6;129-Vmn1r50<sup>tm1Dlc</sup>/J

Stock No: 025198

Protocol 17916: Separated PCR Assay - Vmn1r50&lt;tm1Dlc&gt;

Version 1.0

### Notes

The genotyping protocol(s) presented here have been optimized for reagents and conditions used by The Jackson Laboratory (JAX). To genotype animals, JAX recommends researchers validate the assay independently upon receipt of animals into their facility. Reaction cycling temperature and times may require additional optimization based on the specific genotyping reagents used.

### Expected Results

Mutant = 700 bp

Heterozygote = 700 bp and 250 bp

Wild type = 250 bp

### JAX Protocol

#### Protocol Primers

PRIMER	5' LABEL	SEQUENCE 5' → 3'	3' LABEL	PRIMER TYPE	REACTION	NOTE
20507		TTT CCA AGC AAG GCT GAA GT		Wild type Forward	A	
20508		CCA CAA ATG TTC CCA CTA TGC		Common	A, B	
oIMR6218		CCT TCT ATC GCC TTC TTG ACG		Mutant Forward	B	

#### Reaction A

COMPONENT	FINAL CONCENTRATION
ddH <sub>2</sub> O	
Kapa 2G HS buffer	1.30 X
MgCl <sub>2</sub>	2.60 mM
dNTPS-kapa	0.26 mM
20507	0.50 uM
20508	0.50 uM
Glycerol	6.50 %
Dye	1.00 X
Kapa 2G HS taq polym	0.03 U/ul
DNA	

#### Cycling

STEP	TEMP °C	TIME	NOTE
1	94.0	--	
2	94.0	--	
3	65.0	--	-0.5 C per cycle decrease
4	68.0	--	
5		--	repeat steps 2-4 for 10 cycles (Touchdown)
6	94.0	--	
7	60.0	--	
8	72.0	--	
9		--	repeat steps 6-8 for 28 cycles
10	72.0	--	
11	10.0	--	hold

JAX uses a very high speed Taq (~1000 bp/sec), use cycling times recommended for your reagents.

JAX uses a 'touchdown' cycling protocol and therefore has not calculated the optimal annealing temperature for each set of primers.

## Reaction B

COMPONENT	FINAL CONCENTRATION
ddH2O	
Kapa 2G HS buffer	1.30 X
MgCl2	2.60 mM
dNTPS-kapa	0.26 mM
20508	0.50 uM
oIMR6218	0.50 uM
Glycerol	6.50 %
Dye	1.00 X
Kapa 2G HS taq polym	0.03 U/ul
DNA	

## Cycling

STEP	TEMP °C	TIME	NOTE
1	94.0	--	
2	94.0	--	
3	65.0	--	-0.5 C per cycle decrease
4	68.0	--	
5		--	repeat steps 2-4 for 10 cycles (Touchdown)
6	94.0	--	
7	60.0	--	
8	72.0	--	
9		--	repeat steps 6-8 for 28 cycles
10	72.0	--	
11	10.0	--	hold

JAX uses a very high speed Taq (~1000 bp/sec), use cycling times recommended for your reagents.

JAX uses a 'touchdown' cycling protocol and therefore has not calculated the optimal annealing temperature for each set of primers.

